



(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
02.05.2001 Bulletin 2001/18

(51) Int. Cl.⁷: **H01L 27/00**

(21) Application number: **00123050.7**

(22) Date of filing: **24.10.2000**

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
 Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **28.10.1999 JP 30624599**

(71) Applicant: **SONY CORPORATION**
Tokyo (JP)

(72) Inventors:
 • **Yamada, Jiro,**
c/o Sony Corporation
Tokyo (JP)
 • **Sasaoka, Tatsuya,**
c/o Sony Corporation
Tokyo (JP)


- **Sekiya, Mitsunobu,**
c/o Sony Corporation
Tokyo (JP)
- **Sano, Naoki,**
c/o Sony Corporation
Tokyo (JP)
- **Chiba, Yasuhiro,**
c/o Sony Corporation
Tokyo (JP)
- **Hirano, Takashi,**
c/o Sony Corporation
Tokyo (JP)
- **Iwase, Yuichi,**
c/o Sony Corporation
Tokyo (JP)

(74) Representative:
MÜLLER & HOFFMANN Patentanwälte
Innere Wiener Strasse 17
81667 München (DE)

(54) **Display apparatus and method for fabricating the same**

(57) An active-matrix-type display apparatus ensuring sufficient luminous intensity of display devices within a display plane and allowing improved display properties is provided. Such display apparatus having of a plurality of pixels comprises a lower electrode formed on a substrate; organic layers formed on the lower electrode; and an upper common electrode formed on the organic layers; in which a plurality of the pixels are partitioned by a rib larger in the thickness than the organic layers and having at least a conductive material layer; and the conductive material layer is electrically connected to the upper common electrode.

FIG. 1



Description

BACKGROUND OF THE INVENTION

1. Field of the Invention

[0001] The present invention relates to a display apparatus which comprises organic electro-luminescence devices individually having an organic light emitting layer, and a method for fabricating such display apparatus.

2. Description of the Related Art

[0002] An organic electro-luminescence (abbreviated as EL hereinafter) device based on electro-luminescence of organic materials has an organic layer comprising an organic hole transport layer and an organic light emitting layer laminated between a lower electrode and an upper electrode, and is attracting a good deal of attention as a light emitting device capable of high-luminance light emission by low-voltage direct current drive.

[0003] Since such an organic EL device can respond as fast as within 1 μ sec or below, an organic EL display apparatus using such devices can be driven by simple-matrix duty operation. A problem will, however, arise in that there is a growing need for instantaneously applying a large current to the organic EL devices to ensure sufficient luminous intensity in the future situation in which the EL display apparatus will be operated at a higher duty responding to an increasing trend in the number of pixels, which is likely to damage the devices.

[0004] On the other hand in active-matrix operation, operation current can constantly be applied to the organic EL devices during a period of one frame according to signal voltage, since the signal voltage can be retained by a retention capacitor provided to the individual pixels together with a thin film transistor (abbreviated as TFT hereinafter). Thus, unlikely to a case with the single matrix operation, there is no need to instantaneously apply a large current so that the damages to the organic EL devices can be reduced.

[0005] In the active-matrix display apparatus using such organic EL devices (that is, the organic EL display), each pixel on a substrate is individually provided with a TFT, the TFTs are covered with an interlayer insulating film, and further thereon organic EL devices are formed. Each organic EL device comprises a lower electrode patterned for the individual pixels so as to be connected to the TFT, an organic layer formed so as to cover the lower electrode, and an upper electrode provided so as to cover the organic layer.

[0006] In such an active-matrix display apparatus, the upper electrode is formed as a so-called blanket film covering all pixels, and used as an upper common electrode for such all pixels. In the display apparatus capable of color display, the organic layers are separately

patterned for each color on the lower electrode.

[0007] Such display apparatus having organic EL devices on the insulating film covering the TFTs on the substrate is, however, disadvantageous in that such TFTs are causative of narrowing the aperture of the organic EL devices when the display apparatus is designed as of transmission type in which light emitted from the organic layer is observed from the substrate side.

[0008] Thus for the active-matrix display apparatus, it is supposed to be advantageous to adopt a so-called upper light withdrawing structure (hereinafter referred to as top emission type) in which the light is withdrawn from an opposite side of the substrate so as to ensure a sufficient aperture of the organic EL devices.

[0009] Constituting the active-matrix display apparatus as the top emission type requires the lower electrode to be made of a light reflective material and the upper common electrode to be made of a transparent material. Indium tin oxide (ITO) and indium zinc oxide (IXO), known as materials for transparent conductive film, are however higher in resistivity than metals, so that the upper common electrode is likely to cause voltage drop due to internal voltage gradient occurs therein. This may cause significant degradation of the display properties since the voltage applied to the individual organic EL devices on the display plane becomes non-uniform, and since the luminous intensity in the center portion of the display plane decreases.

[0010] While the transparent conductive film such as ITO or IXO can be formed by evaporation or sputtering, the former method is difficult to yield a film of good quality, and the obtained film tends to have high resistivity and low light transmissivity. The sputtering is thus adopted in the fabrication process of the display apparatus to form the transparent conductive film. The sputtering is, however, higher in energy of particles to be deposited as compared with vapor deposition, so that the underlying surface on which the deposition proceeds is more likely to be damaged. Since the basic structure of the organic EL device resembles to that of a light emitting diode made of inorganic semiconductor materials, such damages exerted on the underlying organic layer will be causative of leak current, which may further result in the production of non-emissive pixels called "dead pixels".

[0011] To avoid the production of such dead pixels, it is proposed to form the upper common electrode with a metal film thin enough so as to allow sufficient light transmissivity. Such metal film may, however, inevitably has a high sheet resistance as a result of the thinning and will also produce voltage gradient in the upper common electrode similarly to the case with the transparent conductive film, which will cause voltage drop and thus will significantly lower the display properties.

[0012] The thinning of the upper common electrode raises another problem in that the electrode cannot fully prevent the atmospheric moisture or oxygen from

intruding into the organic layer, which will accelerate deterioration of the organic layer.

SUMMARY OF THE INVENTION

[0013] It is therefore an object of the present invention to provide an active-matrix-type display apparatus ensuring sufficient luminous intensity of the organic EL devices and allowing improved display properties.

[0014] To accomplish the foregoing object, a first aspect of the present invention relates to a display apparatus having a plurality of pixels, which comprises:

a first electrode formed on a substrate;
a light emitting layer formed on the first electrode;
and

a second electrode formed on the light emitting layer, wherein:

the plurality of pixels are partitioned by a rib larger in thickness than the light emitting layer and having at least a conductive material; and the conductive material layer is electrically connected to the second electrode.

[0015] Since the rib having the conductive material serves as an auxiliary wiring for the second electrode, the pressure drop of the second electrode can successfully be suppressed and thus sufficient luminous intensity of the organic light emitting layer of the individual pixels can be retained even when the second electrode is made of a high-resistivity material. Moreover, the rib also serves as a spacer for a mask used for patterning the organic layer, so that there is no need to separately provide the spacer and the auxiliary wiring between every adjacent pixels. This allows space saving between every adjacent pixels and reserve of the pixel area.

[0016] According to a second aspect of the present invention, there is provided a display apparatus having a plurality of pixels, which comprises:

a field effective transistor formed on a substrate and having a first electrode, a second electrode and a third electrode;

an interlayer insulating film formed on the field effective transistor;

a lower electrode connected to the first electrode through an opening formed on the interlayer insulating film;

an organic layer formed on the lower electrode and having a light emitting layer; and

an upper electrode formed on the organic layer, wherein:

the plurality of pixels are partitioned by a rib larger in thickness than the organic layer and having at least a conductive material; and the conductive material layer is electrically connected to the upper electrode.

[0017] According to the display apparatus according to the second aspect of the present invention, sufficient luminous intensity of the organic light emitting layer of all pixels on the display plane can be retained while achieving the space saving between every adjacent pixels to reserve sufficient pixel area by providing between every adjacent pixels the rib which serves as the spacers for the mask used for patterning the organic layer and also as the auxiliary electrode for the upper electrode covering the entire plane of the display plane. This results in improvement in the display properties of an active-matrix-type display apparatus.

[0018] According to a third aspect of the present invention, there is provided a method for fabricating a display apparatus having a plurality of pixels, which comprises:

a step for forming on a substrate a first electrode;
a step for forming between adjacent ones of the plurality of pixels a rib having a conductive material;
a step for placing a mask on the rib, and forming on the first electrode a light emitting layer smaller in thickness than the rib; and
a step for forming a second electrode on the light emitting layer and on the rib.

[0019] According to a fourth aspect of the present invention, there is provided a method for fabricating a display apparatus having a plurality of pixels, which comprises:

a step for forming on a substrate a field effective transistor having a first electrode, a second electrode and a third electrode;
a step for forming on the field effective transistor an interlayer insulating film;
a step for forming an opening to the interlayer insulating film;
a step for forming on the interlayer insulating film a lower electrode connected through the opening to the first electrode;
a step for forming between adjacent ones of a plurality of the pixels a rib having a conductive material;
a step for placing a mask on the rib, and forming on the lower electrode an organic layer having a light emitting layer smaller in thickness than the rib; and
a step for forming on the organic layer an upper electrode and a protective layer made of an insulating material or a conductive material while keeping the organic layer unexposed to the air.

BRIEF DESCRIPTION OF THE DRAWINGS

[0020] The above and other objects, features and advantages of the present invention will become more apparent from the following description of the presently preferred exemplary embodiments of the invention

taken in conjunction with the accompanying drawings, in which:

Fig. 1 is a sectional view of an essential part of a display apparatus according to an embodiment of the present invention;

Fig. 2 is a plan view of an essential part of a display apparatus for explaining the embodiment of the present invention;

Figs. 3A to 3C are sectional views for explaining a fabrication process of the display apparatus shown in Figs. 1 and 2;

Fig. 4 is a sectional view for explaining the fabrication process as continued from Fig. 3C;

Figs. 5A to 5C are sectional views for explaining the fabrication process as continued from Fig. 4;

Fig. 6 is a sectional view for explaining the fabrication process as continued from Fig. 5C;

Fig. 7 is a sectional view for explaining the fabrication process as continued from Fig. 6;

Fig. 8 is a sectional view of an exemplary constitution of a rib; and

Fig. 9 is a plan view of an essential part of another display apparatus according to another embodiment of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENT

[0021] The present invention will be detailed referring to the attached drawings.

[0022] Fig. 1 is a schematic sectional view showing a display area of a display apparatus according to an example of the present invention. Fig. 2 is a schematic plan view showing the display area of the display apparatus shown in Fig. 1. Fig. 1 is a view in section along the line I-I in Fig. 2. Among various structural components which will be explained hereinafter in order from those closer to the lower layer side, Fig. 1 now shows only organic layers **11R**, **11G**, **11B**, an upper common electrode **12** and ribs **14**. The organic EL display apparatus shown in these figures is an active-matrix-type color display apparatus, the constitution of which will be explained with reference also to additional drawings of Figs. 3A, 3B, 3C, 4, 5A, 5B, 5C, 6 and 7 following the fabrication procedures thereof.

[0023] First as shown in Fig. 3A, a thin-film transistor **2** is fabricated for every pixel "a" on a substrate **1**. A gate electrode **3** of the thin-film transistor **2** is connected to a scan circuit not shown. While the thin-film transistor **2** in this figure is expressed as a bottom-gate-type, a thin-film transistor of a top-gate-type is also allowable. For a case that the display device is of top emission type in which emitted light is observed from the opposite side of the substrate **1**, the substrate **1** needs not be limited to those made of transparent materials. Whereas for a case that the display device is of transmission type in which emitted light is observed from the substrate **1** side, the substrate **1** needs be made of a transparent

material.

[0024] Next, on the substrate **1**, a first interlayer insulating film **4** made of silicon oxide or a silicon oxide-base material such as PSG (phospho-silicate glass), that is phosphorus-containing silicon oxide, is formed so as to cover the thin-film transistor **2**. The first interlayer insulating film **4** is then processed to form via holes (not shown) thereon, a wiring **6** is then patterned on the first interlayer insulating film **4** so as to make contact with a source/drain region of the thin-film transistor **2** through the via hole. The wiring **6** is used for a signal line and is made, for example, of aluminum or aluminum-copper alloy.

[0025] Next, as shown in Fig. 3B, a second interlayer insulating film **7** is formed on the first interlayer insulating film **4** so as to cover the wiring **6**, and the second interlayer insulating film **7** is then processed to form via holes **8** thereon, the bottom of which reaches the wiring **6**. The second interlayer insulating film **7** is preferably made of a material film which can readily be planarized such as polyimide film since the film covers the patterned wiring **6**. The second interlayer insulating film **7** is also preferably made of a material film with a small coefficient of water absorption since the second interlayer insulating film **7** is expected to prevent moisture-related deterioration of an organic layer formed later and thereby to retain desirable luminous intensity.

[0026] Thereafter as shown in Fig. 1, organic EL devices **9** are formed on the second interlayer insulating film **7** so as to be aligned to the individual pixels "a". Each of the EL devices **9** comprises a lower electrode **10**, organic layers **11R**, **11G** or **11B**, and an upper common electrode **12** stacked in this order.

[0027] More specifically, first as shown in Fig. 3C, the lower electrode **10** patterned for every pixel "a" is formed on the second interlayer insulating film **7** so as to make contact with the wiring **6** through the via hole **8** formed to the second interlayer insulating film **7**. The lower electrode **10** is used as an anode electrode or a cathode electrode, which is made of a highly reflective material when the display apparatus is designed as a top emission type, whereas made of a transparent material for the display apparatus of transmission type.

[0028] The exemplary display apparatus shown here is a top emission type, in which the lower electrode **10** is used as an anode electrode. The lower electrode **10** is made of a conductive material having a large work function and a large reflectivity of light, such as chromium (Cr), iron (Fe), cobalt (Co), nickel (Ni), copper (Cu), tantalum (Ta), tungsten (W), platinum (Pt) or gold (Au).

[0029] For a case that the display apparatus is of the top emission type and the lower electrode **10** is used as a cathode electrode, the lower electrode **10** is made of a conductive material having a small work function but a large reflectivity of light, such as aluminum (Al), indium (In), magnesium (Mg)-silver (Ag) alloy, lithium (Li)-fluorine (F) compound or lithium-oxygen (O) com-

pound.

[0030] For a case that the display apparatus is of a transmission type and the lower electrode **10** is used as an anode electrode, the lower electrode **10** is made of a conductive material having a large work function and a large transmissivity of light such as ITO or IXO. For a case that the display apparatus is of the transmission type and the lower electrode **10** is used as a cathode electrode, the lower electrode **10** is made of a conductive material having a small work function and a large transmissivity of light.

[0031] Next, as shown in Fig. 4, an insulating film **13** is formed on the second interlayer insulating film **7** so as to cover the periphery of the lower electrode **10**. Thereby the lower electrode **10** is exposed in a window opened to the insulating film **13**. The insulating film **13** is made, for example, of silicon oxide.

[0032] Next on the insulating film **13**, a rib **14**, which is a unique component in the present invention, is formed. The rib **14** is composed of an insulating material layer **14a** and a conductive material layer **14b** stacked thereon, and is formed in a lattice pattern so as to partition the individual pixels "a" over the entire display area (see Fig. 2), and the upper conductive material layer **14b** is used as an auxiliary wiring which will be connected to the upper common electrode **12** (see Fig. 1) patterned later. The insulating material layer **14a** now can be made of an organic insulating material such as polyimide or photoresist, or an inorganic insulating material such as silicon oxide. The conductive material layer **14b** can be made of a low-resistivity conductive material such as aluminum (Al) or chromium (Cr), which may be used individually or in combination.

[0033] The rib **14** is formed so that the top surface of which is higher in the level than those of the organic layers **11R**, **11G** and **11B** (see Fig. 1). Such designing of the rib **14** allows it to serve as a spacer for a mask used when evaporating the organic layers **11R**, **11G** and **11B** on the lower electrode **10** as described in the next process.

[0034] The rib **14** has tapered side walls so as to ensure desirable coverage of the upper common electrode **12** covering such a rib **14** having a certain level of height as described above.

Next, as shown in Figs. 5A, 5B and 5C, the organic layers **11R**, **11G** and **11B** corresponded to each emission color are successively formed on the lower electrode **10** for each pixel "a". More specifically, a metal mask **20** having openings arranged in a pattern corresponded to each color of the pixels is placed on the rib **14** as a spacer, and the individual organic layers **11R**, **11G**, **11B** are successively evaporated on the lower electrode **10**. The individual organic layers **11R**, **11G**, **11B** are formed so as to fully cover the exposed portion of the lower electrode **10**, and are practically composed of, although not shown in the figure, an organic hole transport layer, an organic light emitting layer and an optional organic electron transport layer stacked, as occasion arises, in

this order from the lower electrode **10** side.

[0035] A specific example of formation processes of the individual organic layers **11R**, **11G**, **11B** will be detailed hereinafter.

First as shown in Fig. 5A, the metal mask **20** is placed so that the openings thereof are aligned to the pixels "a" responsible for green light emission, and organic materials are evaporated assisted by resistance heating. That is, a hole injection layer of 25 nm thick is formed by evaporating m-MTDATA [4,4',4''-tris(3-methylphenyl-phenylamino) triphenylamine], a hole transport layer of 30 nm thick is formed by evaporating α -NPD [4,4-bis(N-1-naphthyl-N-phenylamino)biphenyl], and a light emitting layer of 50 nm thick also serves as an electron transport layer is formed by evaporating Alq3 [tris(8-quinolinolato)aluminium (III)]. These three layers are evaporated in a continuous manner within a single chamber of an evaporation apparatus.

Next as shown in Fig. 5B, the metal mask **20** is placed so that the openings thereof are aligned to the pixels "a" responsible for blue light emission, and organic materials are evaporated assisted by resistance heating. That is, a hole injection layer of 18 nm thick is formed by evaporating m-MTDATA, a hole transport layer of 30 nm thick is formed by evaporating for example α -NPD, a light emitting layer of 14 nm thick also serves as a hole blocking layer is formed by evaporating Bathocuproine (2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline), and a light emitting layer of for example 30 nm thick is formed by evaporating Alq3. These four layers are evaporated in a continuous manner within a single chamber of an evaporation apparatus.

Further as shown in Fig. 5C, the metal mask **20** is placed so that the openings thereof are aligned to the pixels "a" responsible for red light emission, and organic materials are evaporated assisted by resistance heating. That is, a hole injection layer of 55 nm thick is formed by evaporating m-MTDATA, a hole transport layer of 30 nm thick is formed by evaporating for example α -NPD, a light emitting layer is formed by evaporating BSB-BCN [2,5-bis {4-(N-methoxyphenyl-N-phenylamino)styryl} benzene-1,4-dicarbonitrile], and an electron transport layer of 30 nm thick is formed by evaporating Alq3. These four layers are evaporated in a continuous manner within a single chamber of an evaporation apparatus.

[0036] After the organic layers **11R**, **11G**, **11B** are thus formed, an upper common electrode **12** is commonly formed for all pixels so as to cover the entire surface of the display area as shown in Fig. 6. The upper common electrode **12** is formed so as to cover the rib **14** having the tapered side walls and so as to be connected to the conductive material layer **14b** composing the upper portion of the rib **14**, but isolated from the lower electrode **10** by the organic layers **11R**, **11G**, **11B** and the insulating film **13**.

[0037] The upper common electrode **12** is used as an anode electrode or a cathode electrode, and is made

of a transparent material when the display apparatus is designed to be of the top emission type, whereas made of a highly reflective material when the display apparatus is designed to be of the transmission type. The upper common electrode **12** is preferably formed by a method such as evaporation or chemical vapor deposition, in which energy of particles to be deposited is small enough to avoid adverse influences on the underlying layer. It is also preferable to form the upper common electrode **12** successively from the processes for forming the organic layers **11R**, **11G**, **11B** in the same chamber of the deposition apparatus, so as to avoid deterioration of the organic layers **11R**, **11G**, **11B** due to the atmospheric moisture.

[0038] In such constitution of the display apparatus of top emission type having the lower electrode **10** serves as an anode electrode, the upper common electrode **12** is used as a cathode electrode. It is now preferable to form the upper common electrode **12** with a transparent material having a small work function, so as to allow efficient injection of electrons into the organic layers **11R**, **11G**, **11B**, and more preferably with a metal film which can be formed by a film forming method such as vapor deposition in which energy of particles to be deposited is relatively small. The upper common electrode **12** is now formed with a metal film such as Mg-Ag alloy high in light transmissivity and preferably having that of 30% or above, which can be attained by forming the Mg-Ag alloy in a thickness of 14 nm.

[0039] When the lower electrode **10** is used as a cathode electrode, the upper common electrode **12** serves as an anode electrode. The upper common electrode **12** in such a case is preferably made of a transparent material having a large work function, and preferably made of a metal film which can be formed by evaporation method.

[0040] On the other hand, when the display apparatus is of transmission type and the upper common electrode **12** is used as a cathode electrode, the upper common electrode **12** is made of a conductive material having a small work function and a high light reflectivity. When the display apparatus is of transmission type and the upper common electrode **12** is used as an anode electrode, the upper common electrode **12** is made of a conductive material having a large work function and a high light reflectivity.

[0041] After that as shown in Fig. 7, a conductive or insulating protective film **16** is formed on the transparent upper common electrode **12** made of a thin metal film. The protective film **16** is now formed by a method such as evaporation or chemical vapor deposition, in which energy of particles to be deposited is small enough to avoid adverse influences on the underlying layer. It is also preferable to form the protective film **16** successively from the processes for forming the upper common electrode **12** in the same chamber of the deposition apparatus without exposing the upper common electrode **12** to the atmosphere. Thus the protec-

tive layer **16** is formed while preventing the organic layers **11R**, **12G** and **11B** from being degraded due to the atmospheric oxygen or moisture.

[0042] The protective film **16** is further intended for preventing the moisture from reaching the organic layers **11R**, **11G** and **11B**, so that the film **16** needs be made of a material low in moisture permeability and moisture absorption, and made to have a sufficient thickness. When the display apparatus is of the top emission type, the protective film **16** needs be made of a material allowing light emitted from the organic layers **11R**, **11G** and **11B** to pass through, and preferably has a light transmissivity of 80% or above.

[0043] In particular in this case, the protective film **16** is formed using an insulating material. That is, the insulating protective film **16** is directly formed on the upper common electrode **12** simply made a single thin metal film.

[0044] Preferable material for composing such a protective film **16** include inorganic amorphous insulating materials such as amorphous silicon (α -Si), amorphous silicon carbide (α -SiC), amorphous silicon nitride (α -Si_{1-x}N_x) and amorphous carbon (α -C). Such inorganic amorphous insulating materials can compose an excellent protective film **16** due to their low moisture permeability by virtue of their grain-free texture.

[0045] For a case that amorphous silicon nitride is intended as a material for the protective film **16**, the film is formed by the CVD method in a thickness of 2 to 3 μ m. It is now preferable to set the film forming temperature at the normal temperature so as to avoid lowering in the luminous intensity due to deterioration of the organic layers **11R**, **11G**, **11B**, and it is also preferable to form the protective film **16** under a condition allowing the film stress to be minimized so as to avoid peel-off of the protective film **16**.

[0046] For a case that the protective film **16** is made with a conductive material, a transparent conductive material such as ITO or IXO can properly be used.

[0047] After the protective film **16** is thus formed, a glass substrate **18** is optionally fixed thereon using an ultraviolet curing resin layer **17** as shown in Fig. 1, thereby to finish the display apparatus.

[0048] In the thus fabricated organic EL display, the upper common electrode **12** is connected with the rib **14** provided over the entire area of the display plane and serving as an auxiliary wiring therefor, so that the voltage gradient of the upper common electrode **12** formed so as to blanket the display plane can be suppressed, thereby to prevent the voltage drop. This successfully ensures sufficient luminous intensity of the organic EL device **9** provided for each pixel "a" in the display plane.

[0049] In particular in the display apparatus of the top emission type, the sheet resistance of the upper common electrode **12** will rise if it is made of a thin metal film allowing the light emitted from the organic layers **11R**, **11G**, **11B** to pass through. The conductive material layer **14b** of the rib **14** can, however, serve as

an auxiliary wiring for the upper common electrode **12** and can suppress the voltage gradient of such upper common electrode **12** within the display plane, so that the voltage drop at around the center of the display plane can be suppressed.

[0050] Such constitution allows sufficient luminous intensity of the organic EL device **9** provided for the individual pixels "a" within the display plane, even if the protective film **16** made of an insulating material is directly formed on the upper common electrode **12** made of a thin metal film. Such upper common electrode **12** made of a thin metal film and the protective film **16** made of an insulating material can be formed by a method such as evaporation or chemical vapor deposition, in which energy of film-forming particles to be deposited is small enough to avoid adverse influences on the underlying layer, so that damages to the organic layers **11R**, **11G**, **11B** can be avoided. This will prevent leak current from being generated, and will thus prevent the production of non-emissive pixels called "dead pixels" from being produced.

[0051] Moreover, since the rib **14** is used not only as the auxiliary wiring but also as the spacer for the mask **20** used for patterning the organic layers **11R**, **11G**, **11B**, there is no need to separately provide the spacer and the auxiliary wiring between every adjacent pixels "a". This allows space saving between every adjacent pixels "a" and reserve of the pixel area. This successfully results in improving the display property of the active-matrix organic EL display apparatus of the top emission type.

[0052] Connecting the auxiliary wiring (rib **14**) to the high-resistivity upper common electrode **12** also allows power saving of the display apparatus, and ensures desirable display property. This is also beneficial in that retaining desirable display property since heat generation from the upper common electrode **12** can be suppressed and thus the organic layers **11R**, **11G**, **11B** can be prevented from being degraded.

[0053] The rib **14** has a double-layered structure composed of the insulating material layer **14a** and the conductive material layer **14b** stacked thereon, and the height of the rib **14** sufficient for functioning as a spacer is ensured by the insulating material layer **14a**. Thus the rib **14** required to have a certain height can readily be formed without producing etching residual of the conductive material layer **14b**.

[0054] While in the above embodiment the rib **14** was explained as such that a double-layered structure in which the conductive material layer **14b** is stacked on the insulating material layer **14a**, the rib **14** may also be composed of another double-layered structure in which the insulating material layer **14a** is stacked on the conductive material layer **14b** as shown in Fig. 8. While being not shown, the surface of the insulating material layer may be covered with a conductive material layer, or the rib **14** may be composed only of a conductive material layer. Composing the rib **14** only of the conduc-

tive material layer allows the rib **14** and the upper common electrode **12** connected thereto to be lowered in the resistivity.

[0055] It is preferable that the rib **14** of any constitution described above preferably has the tapered sidewalls. Of course in any constitution of the rib **14**, the conductive material layer is connected to the upper common electrode **12** of the organic EL device, so as to be composed as an auxiliary wiring of the upper common electrode **12**. And since the rib **14** is formed so as to have a top surface of which higher in the level than the organic layers **11R**, **11G**, **11B**, that the rib **14** can be used as a spacer for the metal mask **20** for defining the pattern during evaporation of such organic layers **11R**, **11G**, **11B**.

[0056] Fig. 9 is a schematic plan view showing a display area of an organic EL display apparatus according to another embodiment of the present invention.

[0057] The organic EL display apparatus shown in Fig. 9 differs from the apparatus shown in Figs. 1 and 2 in that the rib **14'** has a double-layered structure in which an insulating material layer **14a'** having an island pattern and a conductive material layer **14b** used as an auxiliary wiring, while the remaining portions are the same.

[0058] That is, between every adjacent pixels "a" of the organic EL display apparatus, the conductive material layer **14b** is provided in a lattice form, and on every crossing of the lattice an insulating material layer **14a'** patterned in an island form is provided.

[0059] The height of the rib **14'** which is expected to serve as a spacer is ensured by the insulating material layer **14a'**, wherein the sidewalls of the insulating material layer **14a'** being formed in a tapered form so as to allow a desirable coverage of the upper common electrode **12** covering such insulating material layer **14a'**.

[0060] Also in the organic EL display apparatus having the thus-constituted rib **14'**, the voltage drop of the upper common electrode **12** within the display area can be suppressed since the upper common electrode **12** made of a high-resistivity transparent conductive material is connected to the conductive material layer **14b** as an auxiliary wiring provided over the entire display plane. Thus a sufficient luminous intensity of the organic EL devices **9** of the individual pixels "a" within the display plane is ensured. The stacked portion of the insulating material layer **14a'** and the conductive material layer **14b** of the rib **14'** can serve as a spacer for the mask for patterning the organic layers **11R**, **11G**, **11B**, so that there is no need to separately provide the spacer and the auxiliary wiring between every adjacent pixels. This allows space saving between every adjacent pixels and reserve of the pixel area. Thus similarly to the organic EL display apparatus as described in the previous embodiment, the active-matrix organic EL display apparatus of the top emission type can be improved in the display property.

[0061] Since the height of the portion of the rib **14'**

intended for use as a spacer is ensured by the insulating material layer **14a'**, fabrication of such spacer portion in need of having a certain height can easily be formed. In addition, since the insulating material layer **14a'** is patterned into an island form, that the area occupied by the spacer portion in need of having a certain height (and therefore in need of having a certain degree of the bottom area) can be reduced. This allows the conductive material layer **14b** to be formed with a narrower pattern width between every adjacent pixels "a", which can expand the pixel area and improve the display property.

[0062] While the above description was made on the rib **14'** composed of the conductive material layer **14b** and the island-patterned insulating material layer **14a'** formed thereon, another possible case relates to the rib **14'** composed of the island-formed insulating material layer and the conductive material layer overlaps at a part thereof.

[0063] Although the invention has been described in its preferred form with a certain degree of particularity, obviously many changes and variations are possible therein. It is therefore to be understood that the present invention may be practiced otherwise than as specifically described herein without departing from the scope and the spirit thereof.

Claims

1. A display apparatus having a plurality of pixels, comprising:
 - a first electrode formed on a substrate;
 - a light emitting layer formed on said first electrode; and
 - a second electrode formed on said light emitting layer, wherein:
 - said plurality of pixels are partitioned by a rib larger in thickness than said light emitting layer and having at least a conductive material; and
 - said conductive material is electrically connected to said second electrode.
2. The display apparatus as claimed in Claim 1, wherein said rib additionally has an insulating material layer.
3. The display apparatus as claimed in Claim 1, wherein said rib has a mesa-formed section such that the width of which becomes wider toward said substrate.
4. The display apparatus as claimed in Claim 2, wherein said rib has a mesa-formed section such that the width of which becomes wider toward said substrate.
5. The display apparatus as claimed in Claim 1, further comprising:

a protective film made of an insulating material or a conductive material and formed on said second electrode; and
a second substrate stacked on said protective film.

6. The display apparatus as claimed in Claim 5, further comprising a photo-curing resin layer provided between said protective film and said second substrate.
7. The display apparatus as claimed in Claim 1, wherein an insulating film is formed under said rib.
8. The display apparatus as claimed in Claim 1, wherein said rib is formed in an island form.
9. The display apparatus as claimed in Claim 2, wherein said rib is formed in an island form.
10. The display apparatus as claimed in Claim 1, wherein said second electrode is integrally formed over said plurality of pixels.
11. The display apparatus as claimed in Claim 1, wherein said second electrode and the conductive material are individually made of different materials.
12. The display apparatus as claimed in Claim 1, wherein said first electrode is higher in reflectivity of light than said second electrode.
13. A display apparatus having a plurality of pixels, comprising:
 - a field effective transistor formed on a substrate and having a first electrode, a second electrode and a third electrode;
 - an interlayer insulating film formed on said field effective transistor;
 - a lower electrode connected to said first electrode through an opening formed as penetrating said interlayer insulating film;
 - an organic layer formed on said lower electrode and having a light emitting layer; and
 - an upper electrode formed on the organic layer, wherein:
 - said plurality of pixels are partitioned by a rib larger in thickness than said organic layer and having at least a conductive material; and
 - said conductive material is electrically connected to said upper electrode.
14. The display apparatus as claimed in Claim 13, wherein said rib additionally has an insulating material layer.
15. The display apparatus as claimed in Claim 13,

wherein said rib has a mesa-formed section such that the width of which becomes wider toward said substrate.

16. The display apparatus as claimed in Claim 14, wherein said rib has a mesa-formed section such that the width of which becomes wider toward said substrate. 5
17. The display apparatus as claimed in Claim 13, further comprising: 10
 - a protective film made of an insulating material or a conductive material and formed on said second electrode; and 15
 - a transparent substrate stacked on said protective film.
18. The display apparatus as claimed in Claim 17, further comprising a photo-curing resin layer provided between said protective film and said transparent substrate. 20
19. The display apparatus as claimed in Claim 13, wherein an insulating film is formed under said rib. 25
20. The display apparatus as claimed in Claim 13, wherein said rib is formed in an island form.
21. The display apparatus as claimed in Claim 14, wherein said rib is formed in an island form. 30
22. The display apparatus as claimed in Claim 13, wherein said upper electrode is integrally formed over said plurality of pixels. 35
23. The display apparatus as claimed in Claim 13, wherein said upper electrode and said conductive material are individually made of different materials. 40
24. The display apparatus as claimed in Claim 13, wherein said lower electrode is higher in reflectivity of light than said upper electrode.
25. The display apparatus as claimed in Claim 13, wherein said organic layer has an electron transport layer for transporting electrons and a hole transport layer for transporting holes. 45
26. The display apparatus as claimed in Claim 13, wherein said field effective transistor is a field effective transistor of bottom-gate type. 50
27. The display apparatus as claimed in Claim 13, wherein said rib is roughly positioned above the opening. 55
28. A method for fabricating a display apparatus having

a plurality of pixels, comprising:

- a step for forming on a substrate a first electrode;
- a step for forming between adjacent ones of said plurality of pixels a rib having a conductive material;
- a step for placing a mask on said rib, and forming on said first electrode a light emitting layer smaller in thickness than said rib; and
- a step for forming a second electrode on said light emitting layer and on said rib.
29. The method for fabricating a display apparatus as claimed in Claim 28, wherein said rib is made of an insulating material and a conductive material.
30. The method for fabricating a display apparatus as claimed in Claim 28, wherein said rib is formed so as to have a mesa-formed section such that the width of which becomes wider toward said substrate.
31. The method for fabricating a display apparatus as claimed in Claim 29, wherein said rib is formed so as to have a mesa-formed section such that the width of which becomes wider toward said substrate.
32. The method for fabricating a display apparatus as claimed in Claim 28, further comprising:
 - a step for forming on said second electrode a protective film made of an insulating material or a conductive material; and
 - a step for adhering on said protective film a second substrate using a photo-curing resin.
33. The method for fabricating a display apparatus as claimed in Claim 28, further comprising a step for forming an insulating film under said rib.
34. The method for fabricating a display apparatus as claimed in Claim 28, wherein said rib is formed in an island form in the step for forming said rib.
35. The method for fabricating a display apparatus as claimed in Claim 28, wherein said second electrode and said conductive material layer are individually made of different materials.
36. The method for fabricating a display apparatus as claimed in Claim 28, wherein said first electrode is higher in reflectivity of light than said second electrode.
37. A method for fabricating a display apparatus having a plurality of pixels, comprising:

a step for forming on a substrate a field effective transistor having a first electrode, a second electrode and a third electrode;
 a step for forming on said field effective transistor an interlayer insulating film; 5
 a step for forming an opening to said interlayer insulating film;
 a step for forming on said interlayer insulating film a lower electrode connected through said opening to said first electrode; 10
 a step for forming between adjacent ones of said plurality of pixels a rib having a conductive material;
 a step for placing a mask on said rib, and forming on said lower electrode an organic layer having a light emitting layer smaller in thickness than said rib; and 15
 a step for forming on said organic layer an upper electrode and a protective layer made of an insulating material or a conductive material 20 while keeping said organic layer unexposed to the air.

claimed in Claim 37, wherein said lower electrode is higher in reflectivity of light than said upper electrode.

38. The method for fabricating a display apparatus as claimed in Claim 37, wherein said rib is made of an insulating material and a conductive material. 25
39. The method for fabricating a display apparatus as claimed in Claim 37, wherein said rib is formed so as to have a mesa-formed section such that the width of which becomes wider toward said substrate. 30
40. The method for fabricating a display apparatus as claimed in Claim 38, wherein said rib is formed so as to have a mesa-formed section such that the width of which becomes wider toward said substrate. 35
41. The method for fabricating a display apparatus as claimed in Claim 37, further comprising a step for adhering on said protective film a second substrate using a photo-curing resin. 40
42. The method for fabricating a display apparatus as claimed in Claim 37, further comprising a step for forming an insulating film under said rib. 45
43. The method for fabricating a display apparatus as claimed in Claim 37, wherein said rib is formed in an island form in the step for forming said rib. 50
44. The method for fabricating a display apparatus as claimed in Claim 37, wherein said upper electrode and said conductive material layer are individually made of different materials. 55
45. The method for fabricating a display apparatus as

FIG. 1




FIG. 2




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 4




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 6




FIG. 7




FIG. 8




FIG. 9

